

HumiSeal[®] UV40-SOLAR UV Curable Conformal Coating

Technical Data Sheet

HumiSeal[®] UV40-SOLAR is a single component, low viscosity, high solids conformal coating material that has been formulated for use under prolonged exposure to sunlight, without discoloration or degradation. It meets the requirements of SAE-J-1960 standard (QUV accelerated age testing). In addition, the coating possesses excellent chemical resistance, surface hardness, flexibility, moisture resistance and is tack-free after exposure to UV light. A secondary moisture cure mechanism will cure unexposed areas within 2-3 days at ambient conditions. HumiSeal[®] UV40-SOLAR is in full compliance with the RoHS Directive 2011/65/EU.

Properties of HumiSeal[®] UV40-SOLAR

Density	1.06 g/cm ³
Minimum Solids Content	95 %
Maximum Viscosity, per Fed-Std-141, Meth. 4287	650 ± 150 centipoise
Recommended Coating Thickness	25 - 125 microns
Recommended UV Cure*	See curing section below
Shelf Life at Room Temperature, DOM	12 months
Thermal Shock, 50 cycles per MIL-I-46058C	-65°C to 125°C
Glass Transition Temperature - DSC	45°C
Coefficient of Thermal Expansion - TMA	85 ppm/°C below T _g 197 ppm/°C above T _g
Modulus - DMA	10364 MPa @ -40°C 4283 MPa @ 25°C 66 MPa @ 80°C
Dielectric Withstand Voltage, per MIL-I-46058C	>1500 volts
Dielectric Constant, at 1MHz and 25°C per ASTM D150-98	2.5
Dissipation Factor, at 1MHz and 25°C per ASTM D150-98	0.01
Insulation Resistance, per MIL-I-46058C	8.0 x 10 ¹⁴ ohms (800TΩ)
Moisture Insulation Resistance, per MIL-I-46058C	4.7 x 10 ¹⁰ ohms (47GΩ)
Fungus Resistance, per ASTM G21	Pass

*Fusion "H" style bulb recommended

Application of HumiSeal[®] UV40-SOLAR

Conformal coatings can be successfully applied to substrates that have been cleaned prior to coating and also to substrates assembled with low residue, "no clean" assembly materials. Users should perform adequate testing to confirm compatibility between the conformal coating and their particular assembly materials, process conditions and cleanliness level. Please contact HumiSeal[®] for additional information.

Spraying

HumiSeal[®] UV40-SOLAR should be applied by standard selective coating equipment. The source air used for spraying must be dry (a dry inert gas is highly recommended) to prevent premature curing of the secondary cure mechanism. The spraying should be done with adequate ventilation so that the vapor and mist are carried away from the operator.

Brushing

HumiSeal[®] UV40-SOLAR may be applied by brush for rework or touch up only. Brush must be cleaned with solvent promptly after use.

HumiSeal® UV40-SOLAR Technical Data Sheet

Curing

HumiSeal® UV40-SOLAR is a highly cross linked coating. In order to achieve maximum cross linking density, the product must be exposed to the correct spectral output. Humiseal has modelled the performance of UV40-SOLAR using Arc and Microwave based UV curing equipment. The table below outlines the required dosage and irradiance values necessary to render HumiSeal® UV40-SOLAR tack free post UV exposure with both equipment types. Minimum figures should provide a tack free surface. The maximum recommendation represents highest tested values by Humiseal. The cure recommendations may change as curing technology develops.

		Dose J/cm2*			Irradiance W/cm2*		
		UVA	UVB	UVC	UVA	UVB	UVC
Min	Arc System	1.5	1.5	0.40	0.50	0.50	0.10
Min	Microwave System	2.0	2.0	0.40	0.70	0.70	0.15
Max	Arc System	2.8	2.7	0.80	0.90	0.80	0.20
Max	Microwave System	3.0	3.0	0.60	1.15	1.15	0.24

**Values measured with a Powerpuck II UV radiometer*

Heat is also an important component with UV cure, and different systems produce different heat outputs. Higher heat levels allow UV cure at lower dose/irradiance levels. Consequently, Humiseal recommend that curing is discussed with HumiSeal® Technical staff to ensure the exact customer process being used will meet the coating cure requirements. After UV exposure and return to room temperature the coating should be tack free.

HumiSeal® UV40-SOLAR contains a reliable secondary moisture cure mechanism which will cure any shadow areas on the assembly within 7 days at ambient moisture.

HumiSeal® UV40-SOLAR was designed to be cured using a microwave UV oven equipped with an “H” style bulb. Arc systems can cure HumiSeal® UV40-SOLAR however care must be taken during the equipment selection process to ensure minimum dosage and irradiance values obtained will properly cure the coating. Because of the variations possible in curing equipment type and configuration, it is strongly recommended that you contact HumiSeal Technical Support to discuss your equipment and process in detail.

Clean Up

To flush equipment and clean uncured HumiSeal® UV40-SOLAR, non-alcohol based solvents should be used. HumiSeal® Thinner 521 or Thinner 521EU is recommended.

HumiSeal[®] UV40-SOLAR Technical Data Sheet

Rework

HumiSeal[®] UV40-SOLAR is a highly cross linked UV cured coating. The cured film has a high degree of environmental and chemical resistance and will be more difficult to remove than traditional conformal coatings. Thermal displacement, mechanical abrasion and, where available, HumiSeal[®] Stripper 1100 are suitable options for rework of HumiSeal[®] UV40-SOLAR.

Storage

HumiSeal[®] UV40-SOLAR is photosensitive. The product should not be exposed to direct sunlight or full spectrum fluorescent lighting. HumiSeal[®] UV40-SOLAR should be stored away from excessive heat, in tightly closed opaque containers at 0 to 25°C to ensure maximum shelf life is achieved. Prior to use, allow the product to equilibrate for 24 hours at room temperature. HumiSeal[®] UV40-SOLAR is a moisture curing material and care should be taken to protect process vessels and partial containers from moisture. Partial containers must be purged with a dry, inert gas such as dry air, nitrogen or argon before closure, otherwise premature polymerization by atmospheric moisture will occur.

Caution

Application of HumiSeal[®] Conformal Coatings should be carried out in accordance with local and National Health and Safety regulations.

Use only in well-ventilated areas to avoid inhalation of vapours or spray. Avoid contact with skin and eyes.

Consult SDS prior to use.

Contact HumiSeal[®]

HumiSeal North America

201 Zeta Drive
Pittsburgh, PA 15238
USA
Tel: +1 412-828-1500
Toll Free (US only): 866-828-5470
sales@humiseal.com

HumiSeal Technical Center

295 University Avenue
Westwood, MA 02090
USA
Tel: +1 781-332-0734
Fax: +1 781-332-0703
techsupport@humiseal.com

HumiSeal Europe

505 Eskdale Road, IQ Winnersh
Berkshire RG41 5TU
UK
Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europesales@chasecorp.com

HumiSeal Europe Support

Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europetechsupport@chasecorp.com

HumiSeal S.A.R.L

4/6 Avenue Eiffel
78420 Carrieres-Sur-Seine
France
Tel: +33 (0) 1 30 09 86 86
Fax: +33 (0) 1 30 09 86 87
humiseal.sarl@chasecorp.com

HumiSeal Asian Support

Tel: 852-9451-6434
Fax: 852-2413-6289
asiatechsupport@humiseal.com

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.